

Radiation cured resin**AM6211D modified epoxy acrylate**

- **Product Overview:**On the basis of standard epoxy, special functional groups are introduced and synthesized to improve its performance. It has good wettability for pigment, high fullness and low viscosity.
- **Characteristics:**Good wettability, low viscosity, high fullness, high reactivity.
- **Scope of application:**Ink
- **Product Specifications.**

Project	Index	testing standards
Appearance	yellowish transparent	Visualization
active ingredient	100%	Theoretical values
Acid value (mg KOH/g)	≤3.0	GB/T 6743-2008
Viscosity mpa.s/25 °C	80-150	GB/T 2794-2013
Functionality	2	Theoretical values

- **Packing specification:** 230KG/drum, iron drum packing
- **Storage Requirements:** Keep the resin in a cool or dry place away from light, and avoid sunlight and heat sources; the storage temperature should not exceed 40°C.
- **Shelf life:**At least half a year under normal conditions.
- **Avoid touching skin, eyes and clothes, and wear protective gloves during operation;** In case of leakage, wipe it with cloth and clean it with ethyl acetate; Please refer to MSDS for detailed instructions; Each batch of goods can be put into production only after being tested.